

TWO COLOURS



ONE DIRECTION

Polyethylene

## TIPELIN 6000B

Bimodal HDPE for Blow Moulding

\*\*\*\*\*

### Description

**TIPELIN 6000B** is a high density bimodal polyethylene intended for blow moulding of products with high stiffness and very good environmental stress crack resistance (ESCR).

### Applications

**TIPELIN 6000B** is recommended for household and industrial chemicals such as detergents, cleaners, motor oils etc. **TIPELIN 6000B** is recommended for bottles and containers up to 10 litres.

### Suitability

The product complies with FDA, BfR (BgVV) and EU norms. With regard to the executed tests, the product meets the requirements of the European Pharmacopoeia 5. (3.1.5.)

### Physical Properties

	Test method	Unit	Value/ Tolerance limit	Note
MFR (2.16 kg/190°C)	ISO 1133/B	g/10 min	0.30 (0.25-0.35)	guaranteed
MFR (5.0 kg/190°C)	ISO 1133/B	g/10 min	1.30 (1.10-1.50)	guaranteed
Density	ISO 1183-2	g/cm <sup>3</sup>	0.958 (0.956-0.960)	guaranteed
NNI	2-04		>60	guaranteed
Yellowness Index	ASTM D 1925		max. +2	guaranteed
Granulate impurity	2-12	n/kg	max. 5	guaranteed
Tensile strength at yield *	ISO 527	MPa	30	informative
Tensile strain at yield*	ISO 527	%	11	informative
Tensile strain at break*	ISO 527	%	1000	informative
Flexural modulus*	ISO 178	MPa	1450	informative
Izod impact strength (notched 23°C)*	ISO 180/1A	KJ/m <sup>2</sup>	6	informative
Shore D hardness*	ISO 868	-	64	informative
ESCR (10% AntaroX) F50*	ASTM D 1693	h	300	informative

\*Typical properties, not to be used for specification work

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Slovnaft provide infinite opportunities

MEMBERS OF THE MOL GROUP



Slovnaft  
PETROCHEMICALS



### Processing

**TIPELIN 6000B** is easy to extrude and can be used in all conventional blow-moulding machines.

Recommended processing temperature 170 – 190 °C.

Temperature

Barrel: 170-190°C

Die: 175-190°C

### Storage and Handling

**TIPELIN 6000B** should be stored in dry conditions at temperatures below +50°C and protected from UV light.

Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of the product.

**TIPELIN 6000B** should be protected from contact with direct flames and other ignition sources.

### Safety

See MSDS

### Recycling

The product is suitable for recycling using modern methods of shredding and cleaning.

In-house production waste should be kept clean to facilitate direct recycling.

### Notes

The information provided in this publication has been compiled to the best of our present knowledge. However, in view of the various applications of polyethylene resins and the equipment used, the processing conditions may differ.

The recommendations and data herein are to be construed as informatory only and do not relieve users from carrying out their own tests and experiments prior to processing in order to check suitability for a specific use. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed. Our products are under continuous development, therefore we reserve the right to change the information presented in this brochure at our own discretion.

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Slovnaft provide infinite opportunities

MEMBERS OF THE MOL GROUP



**MANUFACTURER**

Tiszai Chemical Group Plc.  
Polymer Business Unit  
H-3581 Tiszaújváros,  
P.O. Box: 20  
Hungary  
**Internet:** <http://www.tvk.hu>  
**E-mail:** [tvkinfo@tvk.hu](mailto:tvkinfo@tvk.hu)

**CUSTOMER SERVICE**

Tiszai Chemical Group Plc.  
Polymer Marketing and Sales  
Customer Service  
H-3581 Tiszaújváros,  
P.O. Box: 20  
Hungary

**Telephone:** +36 49 522-141, + 36-49 521-366  
+ 36 49 521-367, + 36-80 204-249 (PE),  
+ 36 49 522-013, + 36-49 522-842, + 36-80 204-248 (PP)  
**Fax:** + 36 49 521-186(PE)  
+ 36-49 522-865 (PP)

**SALES ORGANIZATION**

Tiszai Chemical Group Plc.  
Polymer Marketing and Sales  
Sales Department  
H-3581 Tiszaújváros,  
P.O. Box: 20  
Hungary

**Telephone:** +36 49 521-355  
**Fax:** +36 49 522-410  
**E-mail:** [polymersales@tvk.hu](mailto:polymersales@tvk.hu)

**TIPELIN TIPOLEN TIPPLEN TATREN BRALEN**

The joint product portfolio of TVK and Slovnaft provide infinite opportunities

**MEMBERS OF THE MOL GROUP**



**TVK Inter-Chemol GmbH.**  
Felnerstrasse 5.  
D-60322 Frankfurt am Main  
Germany  
**Telephone:** +49 69 154 04 12  
**Fax:** +49 69 154 04 41  
**E-mail:** gaboragoston@tvkic.de

**TVK Italia S.r.L.**  
Via P. Teulié 1.  
20136 Milano  
Italy  
**Telephone:** +39 02 58 30 5779  
**Fax:** +39 02 58 30 3492  
**E-mail:** tvkitaly@energy.it

**TVK-France**  
182, avenue Charles DeGaulle  
F-92200 Neuilly-sur-Seine  
France  
**Telephone:** +33 14 745 63 60  
**Fax:** +33 14 745 45 10  
**E-mail:** kacsandi@free.fr

**TVK UK Ltd.**  
707 High Road, North Finchley  
London N12 0BT  
Great-Britain  
**Telephone:** +44-020/8369 5650  
**Fax:** +44-020/8369 5656/7  
**E-mail:** dios@tvkuk.com

**MOL- Austria Handels GmbH.**  
Gartenbaupromenade 2/6  
A-1010 Wien  
Austria  
**Telephone:** +43 1 515 991 120  
**Fax:** +43 1 513 37 55 1120  
**E-mail:** petchem@mol-vie.com

**TVK Polska Sp.z.o.o.**  
ul. Wawozowa 23/12  
PL-02-796 Warszawa  
Poland  
**Telephone:** +48 22 648 17 95  
**Fax:** +48 22 648 67 94  
**E-mail:** tvkpolska@tvkpolska.pl

**MOL GROUP Moscow**  
Representative Office TVK  
RU-115054 Moscow  
Kosmodamianskaya Naberezhnaya  
D.52 Strojenie 3  
**Telephone:** +7 495 363 39 55  
**Fax:** +7 495 363 39 46  
**E-mail:** tvksn@molmow.ru

**TVK Ukraine**  
04073 Kiev  
pr. Moskovsky, 6  
**Telephone:** +380 44 4683261  
**Fax:** +380 44 4681562  
**E-mail:** tvk@letter.kiev.ua

**SC. MOL Romania P.P. SRL**  
4-6. D. Danielopolu str.  
District 1, 014 134  
Bucharest, Romania  
**Telephone:** +40 21 204 85 00  
+40 21 204 85 02  
**E-mail:** ematei@molromania.ro

July 2006

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Slovnaft provide infinite opportunities

MEMBERS OF THE MOL GROUP

