



Moplen HP565K

Polypropylene, Homopolymer

Product Description

Basell Australia's Polypropylene grade HP565K is a medium flow homopolymer with a modified molecular weight distribution and is formulated with an enhanced process stability additive package. HP565K has been developed for the manufacture of high tenacity wearing tapes, ropes and twines.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	Asia-Pacific, Australia/NZ
Features	Medium Flow, Homopolymer
Typical Customer Applications	Raffia/Tapes/Strapping

Typical Properties	Method	Value	Unit
Physical			
Density (Method D)	ISO 1183	0.90	g/cm ³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	3.5	g/10 min
Mechanical			
Tensile Stress at Yield	ISO 527-1, -2	31.0	MPa
Flexural modulus	ISO 178	1250	MPa
Impact			
Notched izod impact strength (23 °C, Type 1, Notch A)	ISO 180	3.5	kJ/m ²
Hardness			
Shore hardness (Shore D)	ISO 868	73	
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	75	°C
Heat deflection temperature A (1.80 MPa) Unannealed	ISO 75A-1, -2	51	°C
Vicat softening temperature (Method A)	ISO 306	155	°C

Additional Properties

Suitable for the production of articles for food contact use. As supplied in natural form, meets the requirements of Australian Standard 2070 - 1999, "Plastics Materials for Food Contact Use". The base

polymer complies with the United States of America Food and Drug Administration (FDA) Code of Federal Regulations 21 CFR177.1520 (a)(1) and (c)1.1. All other components used in the formulation meet the relevant FDA requirements for use in food contact applications. Conformity with these requirements should not be assumed for other variants and should be investigated with the appropriate supply source.

Notes

Typical properties; not to be construed as specifications.

Copyright 2009 Basell Service Company B.V. All rights reserved.

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyondellbasell.com/>.

Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under LyondellBasell's or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of LyondellBasell except in a writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, incidental, punitive or exemplary damages.

CRP, Adflex, Adstif, Adsyl, Akoalit, Akoafloor, Avant, Catalloy, Clyrell, Dexflex, Entegrity, Get in touch with, Hifax, Higran, Histif, Hostacom, Hostalen, Indure, Koattro, LIPP, Lucalen, Luflexen, Lupocomp, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Moplen, Pristene, Purell, Pro-fax, Sequel, Sholybox, Softell, Spherilene, Spheripol, Spherizone, Stretchene, Topyyl and Valtec are trademarks owned or used by LyondellBasell group companies.

Adflex, Adstif, Adsyl, Akoalit, Akoafloor, Avant, Clyrell, CRP, Dexflex, Hifax, Hostacom, Hostalen, Indure, Koattro, Lucalen, Moplen, Purell, Pro-fax, Sequel, Softell, Spheripol, Spherizone and Topyyl are registered in the U.S. Patent and Trademark Office.

Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.

Release Date: 28 Sep 2007