



Alathon®

L5005

High Density Polyethylene

HMW Film Grade

Melt Index 0.057 Density 0.949

- Applications** ALATHON L5005 is a high molecular weight high density copolymer that provides broad bimodal molecular weight distribution, high stiffness and good heat seal response and strength. Typical applications include merchandise bags, grocery sacks, trash can liners, produce bags and roll stock.
- Regulatory Status** L5005 meets the requirements of the Food and Drug Administration regulation 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information.
- Processing Techniques** Specific recommendations for processing L5005 can only be made when the processing conditions, equipment and end use are known. For further suggestions please contact your Equistar sales representative.

Typical Properties	Property	Nominal Value	Units	ASTM Test Method
	Melt Index	0.057	g/10 min	D 1238
	Density	0.949	g/cc	D 1505
	Total Energy Dart Drop	2.05	ft-lbs/mil	D 4272
	Elmendorf Tear Strength, MD (TD)	14 (35)	g	D 1922
	Tensile Strength @ Yield, MD (TD)	3,800 (3,400)	psi	D 882
	Tensile Strength @ Break, MD (TD)	8,500 (5,000)	psi	D 822
	Elongation @ Break, MD (TD)	300 (420)	%	D 882
	Secant Modulus, MD (TD)	115,000 (140,000)	psi	D 882

Typical Process Condition Ranges:

BUR=3.5-4.5:1; Neck Height=6-9 Die Diameters; Die Gap (nominal), in.=0.040-0.050;
Tower Height=Relatively Short; Output, Lb/Hr/In of Die Circumference=10-12;
Melt Temperature - 390-420°F (199-216°C)

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.

* Alathon is a registered trademark of Equistar Chemicals, LP.