



Hostalen ACP 5831 D

Polyethylene, High Density

Product Description

Hostalen ACP 5831 D is a high density polyethylene with an excellent combination of stiffness and stress crack resistance. It is delivered in pellet form containing antioxidants and designed for small bow moulding applications in the food and consumer segment and for toys.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	Europe
Processing Method	Extrusion Blow Moulding
Features	Antioxidant, ESCR, High (Stress Crack Resist.), Rigidity, High
Typical Customer Applications	Blow Moulding Applications, Sports, Leisure and Toys, Consumer Packaging

Typical Properties	Method	Value Unit
Physical		
Density	ISO 1183	0.959 g/cm ³
Melt flow rate (MFR)	ISO 1133	
(190°C/2.16kg)		0.25 g/10 min
(190°C/21.6kg)		21 g/10 min
(190°C/5.0kg)		1.2 g/10 min
Bulk density	ISO 60	>0.500 g/cm ³
Mechanical		
Tensile Modulus	ISO 527-1, -2	1320 MPa
Tensile Stress at Yield	ISO 527-1, -2	28.0 MPa
Tensile Strain at Yield	ISO 527-1, -2	10 %
Tensile Impact Strength	ISO 8256	75.0 kJ/m ²
<i>Note: notched</i>		
Impact		
Charpy notched impact strength (-30 °C, Type 1, Notch A)	ISO 179	11.0 kJ/m ²
Hardness		
Shore hardness (Shore D)	ISO 868	63
Ball indentation hardness (H 132/30)	ISO 2039-1	53.0 MPa
Thermal		
Vicat softening temperature (B50 (50°C/h 50N))	ISO 306	79.0 °C
Film		
Melt Temperature		180 to 220 °C

Notes

Typical properties; not to be construed as specifications.

Additional Properties

Staudinger Index Jg, ISO 1628: 260 ml/g FNCT: 3.5 MPa, 2% Arcopal, 80°C, ISO 16770: 8 h
ESCR - Basell bottle test: 45 h

Further Information

Hostalen ACP 5831 D

Conveying: Conveying equipment should be designed to prevent production and accumulation of fines and dust particles that are contained in polymer resins. These particles can under certain conditions pose an explosion hazard. We recommend the conveying system used is equipped with adequate filters, is operated and maintained that no leak develops and adequate grounding exists at all times.

Health and Safety:

The resin is manufactured to the highest standards but, special requirements apply to certain applications such as food end-use contact and direct medical use. For specific information on regulatory compliance contact your local representative.

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal precaution to prevent mechanical or thermal injury to the eyes.

Molten polymer may be degraded if it is exposed to air during any of the processing and off-line operations. The products of degradation have an unpleasant odour. In higher concentrations they may cause irritation of the mucus membranes. Fabrication areas should be ventilated to carry away fumes or vapours. Legislation on the control of emissions and pollution prevention must be observed. If the principles of sound manufacturing practice are adhered to and the place of work is well ventilated, no health hazards are involved in processing the resin.

The resin will burn when supplied with excess heat and oxygen. It should be handled and stored away from contact with direct flames and/or ignition sources. In burning the resin contributes high heat and may generate a dense black smoke. Starting fires can be extinguished by water, developed fires should be extinguished by heavy foams forming an aqueous or polymeric film. For further information about safety in handling and processing please refer to the Material Safety Data Sheet.

Storage:

The resin is packed in 25 kg bags or in bulk containers protecting it from contamination. If it is stored under adverse conditions, i. e. if there are large fluctuations in ambient temperature and the atmospheric humidity is high, moisture may condense inside the packaging. Under these circumstances, it is recommended to dry the resin before use. Unfavourable storage conditions may also intensify the resin's slight characteristic odour.

The resin is subjected to degradation by ultra-violet radiations or by high storage temperatures. Therefore the resin must be protected from direct sunlight, temperatures above 40°C and high atmospheric humidity during storage. The resin can be stored over a period of more than 6 months without significant changes in the specified properties, appropriate storage conditions provided. Higher storage temperatures reduce the storage time.

The information submitted is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. The data do not relieve the customer from his obligation to control the resin upon arrival and to complain about faults. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

© 2003 Basell Service Company B.V.

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.basell.com/>.

Before using a LyondellBasell product, customers and other users should make their own independent

determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under LyondellBasell's or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of LyondellBasell except in a writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, incidental, punitive or exemplary damages.

CRP, Adflex, Adstif, Adsyl, Akoalit, Akoafloor, Avant, Catalloy, Clyrell, Entegrity, Get in touch with, Hifax, Higran, Histif, Hostacom, Hostalen, LIPP, Lucalen, Luflexen, Lupocomp, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Moplen, Purell, Pro-fax, Sholybox, Softell, Spherilene, Spheripol, Spherizone, Stretchene, Toppyl and Valtec are trademarks owned or used by LyondellBasell group companies.

Adflex, Adstif, Adsyl, Clyrell, CRP, Hifax, Hostacom, Hostalen, Lucalen, Luflexen, Lupolen, Lupotech, Moplen and *Pro-fax* are registered in the U.S. Patent and Trademark Office.

Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.

Release Date: 03 Apr 2008