



Lupolen 2420 H

Polyethylene, Low Density

Product Description

Product Characteristics

Status	Commercial: Active
Test Method used	ISO ASTM
Availability	Europe, North America, Asia-Pacific, Australia/NZ, Africa-Middle East, Latin America
Processing Method	Cast Film, Blown film
Features	Heat Seal, Good, Optical, Processability, Good
Typical Customer Applications	Bags & Pouches, Film, Shrink Film, Blown Film, Cast Film

Typical Properties	Method	Value Unit
Physical		
Density	ISO 1183	0.924 g/cm ³
Melt flow rate (MFR) (190°C/2.16kg)	ISO 1133	1.9 g/10 min
Mechanical		
Tensile Modulus	ISO 527-1, -2	260 MPa
Tensile Stress at Yield	ISO 527-1, -2	11.0 MPa
Tensile Strength	ISO 527-1, -3	26.0 MPa 18.0 MPa
Tensile Strain at Break	ISO 527-1, -3	250 % 600 %
Hardness		
Shore hardness (Shore D)	ISO 868	48
Ball indentation hardness (H 49/30)	ISO 2039-1	18.0 MPa
Thermal		
Vicat softening temperature (A50 (50°C/h 10N))	ISO 306	94.0 °C
Melting Temperature	ISO 3146	111 °C
Film		
Melt Temperature		160 to 200 °C

Notes

Typical properties; not to be construed as specifications.

Additional Properties

Film properties tested using 50 µm thickness blown film extruded at a melt temperature of 180°C and a blow-up ratio of 2:1.

Failure Energy, DIN 53373, 50µm: 4 J/mm

Coefficient of Friction, ISO 8295: 55%

Recommended Thickness: 20 to 100 µm.

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.basell.com/>.

Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under LyondellBasell's or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of LyondellBasell except in a writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, incidental, punitive or exemplary damages.

CRP, Adflex, Adstif, Adsyl, Akoalit, Akoafloor, Avant, Catalloy, Clyrell, Entegrity, Get in touch with, Hifax, Higran, Histif, Hostacom, Hostalen, LIPP, Lucalen, Luflexen, Lupocomp, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Moplen, Purell, Pro-fax, Sholybox, Softell, Spherilene, Spheripol, Spherizone, Stretchene, Toppyl and Valtec are trademarks owned or used by LyondellBasell group companies.

Adflex, Adstif, Adsyl, Clyrell, CRP, Hifax, Hostacom, Hostalen, Lucalen, Luflexen, Lupolen, Lupotech, Moplen and *Pro-fax* are registered in the U.S. Patent and Trademark Office.

Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.

Release Date: 15 Jun 2004